

Multiflex Coating Spray Black

Art.: 02.1131.5000

Aerosol can 500 ml

Multiflex Coating Spray is a totally PVC-free stone chip protection that provides a perfect anti-corrosion coating and has excellent sound deadening qualities. OEM structures can be perfectly imitated.



Base:	Mixture of rubbers, resins and fillers
Density:	± 970 kg/m ³
Consistency:	Liquid (ready-to-use in aerosol)
Solvents:	Mixture of aromatic and aliphatic solvents
Flash point:	< 0°C
Temperature resistance:	-40°C to +80°C (short-time limit +200°C)
UV resistance:	Good. Slight change in colour may appear.
Water resistance:	Good
Solvent resistance:	Good. Once dry, resistant to hydrocarbons
Tests:	Gitterschnitt: GT0a Stone chip test: 5B = 25 chips (25-49), Diameter: 1-3 mm
Application conditions:	+15°C to +30°C
Type of surface:	Bare and primed metal
Surface preparation:	The surface must be clean, dry and free of dust and grease. Sand the surface. Clean surfaces with Innotec Multisol .
Application method:	Shake can well during at least 2 minutes before use. Spraying distance ± 20 cm. Apply in even layers until the required texture is achieved. Use the special nozzle with the tube. After use, invert can and spray until clear to clean the nozzle.
Dust dry:	After ± 20 minutes (at 20°C / 200µ layer thickness)
Curing time:	After ± 75 minutes (at 20°C / 200µ layer thickness)
Recommended layer thickness:	250µ (wet)
Paintability:	Can be painted over after 10 minutes with almost each solvent based paint system. When using water based paints, Multiflex Coating Spray must be completely cured and lightly sanded with an abrasive cloth (Scotch-Brite Grey) or a P320 sandpaper. Due to the huge variety of paint types on the market, it is best to test the paint beforehand.
Cleaning of materials used:	With Innotec Multisol





Cleaning of hands: With Innotec [Safe Hand Clean Plus](#) and water

Shelf life: 2 years in original, unopened packaging

Type of batchcode: A

EAN Code: 5400563008294

This technical info sheet replaces all previous versions.

All information is supplied without obligation and based on our knowledge and experience with the product under normal conditions. In practice, the information supplied can in no way replace the tests that need to be performed before first use of the product. Only prior testing of the product can prove whether the product is indeed suitable for the intended application (or not). Thus, we cannot accept any responsibility in case our products are not used in compliance with the advices given.

If the product should not meet the quality requirements, we will only reimburse up to a maximum of the purchase price of the product. We accept no responsibility whatsoever and shall under no circumstances be liable for damage or consequential loss arising from the use of the product.

For information concerning safe use and storage, please refer to the safety data sheet of the product concerned.

